

Roller bearing, especially for a vehicle drive shaft bearing unit, e.g. in a differential, has rollers of a carbonitrided, quenched and tempered chromium steel with high carbon, silicon and manganese contents

Publication number: DE19960803

Publication date: 2000-06-21

Inventor: MAEDA KIKUO (JP); NAKASHIMA HIROKAZU (JP);
OKAYAMA AKIO (JP)

Applicant: NTN TOYO BEARING CO LTD (JP)

Classification:

- International: *F16C33/30; F16C33/62; B60K17/16; F16C33/30; F16C33/62; B60K17/16; (IPC1-7): F16C33/34; B60K17/22*

- European: F16C33/30; F16C33/62

Application number: DE19991060803 19991216

Priority number(s): JP19980359409 19981217; JP19980359462 19981217;
JP19980359396 19981217; JP19990159028 19990607;
JP19990159147 19990607; JP19990159154 19990607;
JP19990175761 19990622

Also published as:



US6423158 (B1)

FR2787529 (A1)

Report a data error here

Abstract of DE19960803

Roller bearing has roller elements made of a carbonitrided, quenched and tempered high carbon chromium steel with high silicon and manganese contents. A novel roller bearing has roller elements made of a steel which contains (by wt.) 0.8-1.5% C, 0.4-1.2% Si, 0.8-1.5% Mn and 0.8-1.8% Cr and which has been subjected to carbonitriding, quenching and tempering so that the surface residual austenite content is 20-50 vol.%. An Independent claim is also included for a vehicle drive shaft bearing unit comprising the above roller bearing.

Data supplied from the **esp@cenet** database - Worldwide